



PLASTIFORM® 3201 Isotropic Magnets

PRODUCT DATA SHEET

Typical Properties

Properties	Isotropic	
	CGS/U.S.	SI
Br (Residual Induction)	6,300 Gauss	630 mTesla
Hc (Coercive Force)	5,300 Oersteds	440 kA/m
Hci (Intrinsic Coercivity)	15,000 Oersteds	1185 kA/m
BHmax (Maximum Energy Product)	9 MGOe	70 kJ/m ³
BrHx (Intrinsic Parameter)	82 MGOe	650 kJ/m ³
Reversible Temperature Coefficient of Induction, Br	-0.07 %/°F	-0.13 %/°C
Reversible Temperature Coefficient of Coercivity, Hci	-0.22 %/°F	-0.40 %/°C
Peak Magnetizing Force Required	35,000 Oersteds	2765 kA/m
Density	0.21 lb/in ³	5.95 g/cc
Recommended Maximum Operating Temperature	250° F	120° C

Features

- Epoxy bonded, Compression molded, isotropic neodymium-iron-boron
- Energy product (BHmax) 9 MGOe
- BrHx of 82 MGOe
- Isotropic, may be magnetized in any direction and pattern


Product Information

- Best suited to simple shapes such as cylinders, discs, and arcs or where maximum MGOe is needed.
- Recommended maximum use temperature of 120° C

All values shown are measured at 23°C (73°F).

All values are based on a standard test plug. Consult with an application engineer for more information on your specific requirements.

Typical Demagnetization Curve @ 23° C (73° F)



All data presented in this document are for general reference only and should not be relied upon to represent standard characteristics, nor are they guaranteed upon use. Dimensions and shape of the magnet, in combination with required manufacturing processes, may cause the magnetic and physical characteristics to vary from typical values. Arnold Magnetic Technologies reserves the right to change information in this document, including magnet performance standards, specifications, and characteristics without notice.

Flexmag Industries

1000 Magnet Drive., Norfolk, NE 68701

Tel: (800) 328-1373 or (+1) 402-371-6100 Fax: (+1) 402-371-8495

www.flexmag.com

A Division of



Warranty

Limited Warranty and Exclusive Remedy

Flexmag Industries, Inc. warrants that these products conform to industry standards specific herein and will be free from defects in material and workmanship. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ANY AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND IN LIEU OF ANY OTHER OBLIGATION ON THE PART OF THE FLEXMAG INDUSTRIES, INC. Flexmag Industries, Inc. will, at its option, repair or replace free of charge (excluding all shipping and handling costs) any products which have not been subject to misuse, abuse, or modification and which in its sole determination were not manufactured in compliance with the warranty given above.

THE REMEDY PROVIDED FOR HEREIN SHALL BE THE EXCLUSIVE REMEDY FOR ANY BREACH OF WARRANTY OR ANY CLAIM ARISING IN ANY WAY OUT OF THE MANUFACTURE, SALE, OR USE OF THESE PRODUCTS. In no event shall Flexmag Industries, Inc. and its parent company, Arnold Magnetic Technologies, be liable for consequential, incidental or any other damages of any nature whatsoever except those specifically provided herein for any breach of warranty or any claim arising in any way out of the manufacture, sale, or use of these products. No other person is authorized by Flexmag Industries, Inc. to give any other warranty, written or oral, *pertaining to the products*.

Flexmag Industries

1000 Magnet Drive., Norfolk, NE 68701
Tel: (800) 328-1373 or (+1) 402-371-6100 Fax: (+1) 402-371-8495
www.flexmag.com