



**Sintered ALNICO
Permanent Magnets**



ALNICO PERMANENT MAGNETS

Introduction

For over 50 years an acknowledged leader in the field of permanent magnets, Arnold Engineering continues its tradition of superior quality and value with the full line of Alnico products presented in this catalog.

One of the oldest members of our magnet family, Alnico remains the workhorse of the permanent magnet industry and can be relied upon to deliver impressive flux density at an economical price. Alnico also boasts the lowest temperature coefficient of any commercial magnet material (.02% per degree centigrade) allowing for excellent stability over a wide temperature range.

Alnico has experienced renewed interest in recent years in such temperature-sensitive applications as hall-effect and MR-based automotive and electronic sensors, in addition to the traditional magnetron, TWT amplifiers, actuators, motors and instruments applications that have long relied upon Alnico.

Call Arnold Engineering today for applications engineering assistance, samples or pricing.

General characteristics

Alnico permanent magnets form a family of alloys whose major constituents are iron, aluminum, nickel and cobalt, though other elements (e.g., copper and titanium) may be included in minor amounts. Grades of Alnico vary in cobalt content, which ranges from zero (Alnico 3) to 40% (Alnico 8).

Lower grades (2, 3 and 4) are unoriented—magnetic properties are isotropic and equal in all directions. Their magnetic output is relatively low. Anisotropic grades (Alnico 5, 6, 8 and 9) are designed to produce high magnetic output in a specified direction. Orientation is achieved during heat treatment, by cooling the product from a temperature of about 2000° F (1093° C) at a controlled rate, within a magnetic field which conforms to the preferred direction of magnetization.

Alnico 5, the most widely used grade, can usually be depended upon to deliver energy to a magnetic circuit more economically than

any of the other Alnico grades. Alnico 8 possesses the highest coercive force of all Alnico grades, as well as excellent energy per unit volume and a low temperature coefficient. It is recommended for applications exposed to strong demagnetizing fields, or where space considerations dictate a short magnetic length.

ArKomax® 800 and Alnico 9 are premium grades of Alnico 5 and 8, respectively. The superior magnetic output of these grades is produced by crystal orientation from the molten state in the desired direction of magnetization.

Manufacturing processes

Alnico magnets can be produced in a wide variety of shapes and sizes, ranging in weight from less than one ounce (28 grams) to over 80 pounds (36 kilograms).

The majority of magnets are cast in sand molds, following melting in a high-frequency induction furnace.

Magnets weighing less than an ounce (28 grams) may be produced by sintering. In this process, the desired mix of metal powders is pressed to shape and size in a die, and then sintered at a temperature of approximately 2300° F (1260° C) in a hydrogen atmosphere. The sintering process is well suited to large volume production and results in parts which are structurally stronger than cast magnets. Relatively close tolerances can be achieved without grinding.

Stock items and tooling

A variety of shapes and sizes in selected grades of Alnico have become standard over the years. A partial list of these parts is provided later in this manual. Arnold maintains the required tooling for these parts and in many cases has quantities of them in stock, ready for immediate shipment.


The use of stock items, especially on small quantity orders, can result in substantial savings to the user because the need for costly production tooling is eliminated.

Sintered Alnico 2, 5, 6

Magnetic and Physical Properties (Typical Values)

	Max. Energy Product $B_d \times H_d$		Residual Induction B_r		Required Magnetizing Field		Coersive Force H_c		Recoil Permeability		Permeance Coefficient B/H @ (BdHd) Max.		Induction at Maximum Energy Product	
	MGOe	KJ/m ³	G	mT	Oe	KA/m	Oe	KA/m	G/Oe	10 ⁻³ Tm/KA	G/Oe	10 ⁻³ Tm/KA	G	mT
Sint. Alnico 2	1.40	11.1	6600	660	2000	160	550	44	5.6	7.0	12.0	15.0	4100	410
Sint. Alnico 5	3.75	29.8	10800	1080	3000	240	600	48	5.2	6.5	17.0	21.5	8000	800
Sint. Alnico 6	3.00	23.9	9400	940	3000	240	780	62	5.4	6.8	12.0	15.0	6000	600

Typical Demagnetization Curves




Sintered Alnico 2, 5, 6

Magnetic and Physical Properties (Typical Values)


	Density		Electrical Resistivity	Tensile Strength		Transverse Modulus of Rupture		Coefficient of Thermal Expansion	Hardness Rockwell C
	lb./in. ³	gr/cm ³	25° C (μΩ cm)	PSI	N/mm ²	PSI	N/mm ²	per ° C x 10 ⁶	
Sint. Alnico 2	0.247	6.84	68	65000	450	70000	480	12.4	51
Sint. Alnico 5	0.253	7.00	50	50000	350	60000	415	11.3	52
Sint. Alnico 6	0.250	6.92	50	55000	380	110000	760	11.3	53

Temperature Effects


Sint. Alnico 2



Sint. Alnico 5



Sint. Alnico 6




Sintered Alnico 8B, 8H

Unoriented Sintered Alnico 8

Magnetic and Physical Properties (Typical Values)

	Max. Energy Product $B_d \times H_d$		Residual Induction B_r		Required Magnetizing Field		Coersive Force H_c		Recoil Permeability		Permeance Coefficient B/H @ (BdHd) Max.		Induction at Maximum Energy Product	
	MGOe	KJ/m ³	G	mT	Oe	KA/m	Oe	KA/m	G/Oe	10 ⁻³ Tm/KA	G/Oe	10 ⁻³ Tm/KA	G	mT
Sint. Alnico 8B	5.00	39.8	8000	800	6000	480	1700	135	1.8	2.3	4.5	5.5	4750	475
Sint. Alnico 8H	5.00	39.8	7000	700	6000	480	1850	147	1.9	2.4	3.4	4.3	4100	410
Unoriented Sint. Alnico 8	2.40	19.1	5500	550	6000	480	1475	117	2.6	3.3	3.8	4.7	3000	300

Typical Demagnetization Curves




Sintered Alnico 8B, 8H & Unoriented Sintered Alnico 8

Magnetic and Physical Properties (Typical Values)


	Density		Electrical Resistivity	Tensile Strength		Transverse Modulus of Rupture		Coefficient of Thermal Expansion	Hardness Rockwell C
	lb./in. ³	gr/cm ³	25° C (μΩ cm)	PSI	N/mm ²	PSI	N/mm ²	per ° C x 10 ⁶	
Sint. Alnico 8B	0.252	6.98	53	55000	380	55000	380	11.6	56
Sint. Alnico 8H	0.252	6.98	53	50000	350	50000	350	11.6	56
Unoriented Sint. Alnico 8	0.252	6.98	53	50000	350	50000	350	11.6	56

Temperature Effects


Sint. Alnico 8B



Sint. Alnico 8H




Unoriented Sint. Alnico 8




Sintered Alnico Stock Magnets

All Sintered Alnico stock magnets listed are furnished in Sintered Alnico 2 except those marked Alnico 5.





CAT. NO.	WT.		DIMENSIONS													
	LBS.	GRAMS	A (Sintered)		A (Ground)		B		C		D		E		F	
			IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM
S2C533	.005	2.27	.322	8.18	.307	7.80	.156	3.96	.125	3.18	.390	9.91	.188	4.78	—	—
S2C534	.006	2.72	.400	10.16	.375	9.53	.169	4.29	.156	3.96	.443	11.25	.193	4.90	—	—
S2C535	.007	3.18	.322	8.18	.307	7.80	.156	3.96	.125	3.18	.390	9.91	.312	7.93	—	—
S2C522	.024	10.90	.405	10.29	.375	9.53	.203	5.16	.250	6.35	.890	22.61	.382	9.70	.120	3.05





CAT. NO.	WT.		DIMENSIONS					
	LBS.	GRAMS	A		B		C	
			IN.	MM	IN.	MM	IN.	MM
S5B558*	.001	.45	.062	1.58	.062	1.58	.500	12.70
S5B559*	.003	1.36	.125	3.18	.125	3.18	.750	19.05
S5B560*	.016	7.26	.240	6.10	.240	6.10	1.125	28.58

* These parts are furnished in Sintered Alnico 5 and are oriented parallel to the C dimension.



CAT. NO.	WT.		DIMENSIONS					
	LBS.	GRAMS	A		B		C	
			IN.	MM	IN.	MM	IN.	MM
S2F572	.004	1.82	.480	12.19	.129	3.28	.086±.002	2.18±.05
S2F573	.016	7.26	.625	15.88	.245	6.22	.250 Sint.	6.35


CAT. NO.	WT.		DIMENSIONS																	
	LBS.	GRAMS	A		B		C		D		E (SINTERED)		E (GROUND)		F		G		H	
			IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM	IN.	MM
S2H584	.002	.91	.250	6.35	.062	1.58	.047	1.19	.055	1.40	.150	3.81	.125	3.18	—	—	—	—	—	—
S2H585	.003	1.36	.312	7.93	.095	2.41	.071	1.80	.050	1.27	.190	4.83	.175	4.45	—	—	—	—	—	—
S2H586	.005	2.27	.400	10.16	.130	3.30	.099	2.52	.093	2.36	.202	5.13	.187	4.75	—	—	—	—	—	—
S2H597	.001	.45	.250	6.35	.103	2.62	.094	2.39	.055	1.40	.156	3.96	.140	3.56	.080	2.03	—	—	.015	.38
S2H598	.003	1.36	.312	7.93	.093	2.36	.062	1.58	.075	1.91	.203	5.16	.190	4.83	.080	2.03	.156	3.96	.015	.38
S2H599	.005	2.27	.400	10.16	.140	3.56	.109	2.77	.100	2.54	.209	5.31	.194	4.93	.090	2.29	—	—	.015	.38
S2H600	.009	4.09	.510	12.95	.156	3.96	.156	3.96	.110	2.79	.250	6.35	.240	6.10	.156	3.96	.312	7.93	.031	.79
S2H601	.011	4.99	.510	12.95	.187	4.75	.062	1.58	.105	2.67	.300	7.62	.272	6.91	.100	2.54	.187	4.75	—	—
S2H602	.018	8.17	.510	12.95	.187	4.75	.062	1.58	.125	3.18	.457	11.61	.442	11.23	.100	2.54	.187	4.75	.062	1.58



Sintered Alnico 8


Rectangles, Washers & Discs

CAT. NO.	DIMENSIONS					
	A		B		C	
	IN.	MM	IN.	MM	IN.	MM
S8B561	.375	9.53	.125	3.18	1.000	25.40
S8B562	.375	9.53	.250	6.35	1.000	25.40
S8B563	.250	6.35	.375	9.53	1.000	25.40
S8B564	.125	3.18	.375	9.53	1.000	25.40





Rectangles

CAT. NO.	DIMENSIONS					
	A		B		C	
	IN.	MM	IN.	MM	IN.	MM
S8F575	.130	3.30	.312	7.93	.125	3.18
S8F576	.210	5.33	.415	10.54	.125	3.18
S8F577	.250	6.35	.525	13.34	.150	3.81
S8F578	.285	7.24	.620	15.75	.200	5.08



Washers

CAT. NO.	DIMENSIONS			
	A		B	
	IN.	MM	IN.	MM
S8A610	.125	3.18	.062	1.58
S8A611	.125	3.18	.125	3.18
S8A612	.125	3.18	.250	6.35
S8A620	.250	6.35	.062	1.58
S8A621	.250	6.35	.125	3.18
S8A622	.250	6.35	.250	6.35
S8A630	.375	9.53	.125	3.18
S8A631	.375	9.53	.250	6.35
S8A632	.375	9.53	.375	9.53
S8A640	.500	12.70	.125	1.58
S8A641	.500	12.70	.250	6.35
S8A642	.500	12.70	.500	12.70



Discs

Standard Alnico Tolerances

Cast Alnico

Dimension		Tolerance	
Up to 1"	Up to 25.4 mm	±1/64"	.40 mm
1" to 3"	25.4 to 76.2 mm	±1/32"	.81 mm
3" to 5"	76.2 to 127.0 mm	±3/64"	1.19 mm
5" to 7"	127.0 to 177.8 mm	±1/16"	1.59 mm
7" to 9"	177.8 to 228.6 mm	±5/64"	1.98 mm

Sintered Alnico

Dimension		Tolerance	
Up to .125"	Up to 3.18 mm	±.005"	.13 mm
.126" to .625"	3.20 to 15.88 mm	±.010"	.25 mm
.626" to 1.250"	15.90 to 31.75 mm	±.015"	.38 mm

Concentricity

Concentricity between inside and outside as cast diameters: .031" (.79 mm) F.I.R. when hole diameter is greater than hole length. 1.5 X total O.D. tolerance F.I.R. when hole diameter is less than hole length.

Squareness

Perpendicularity between one ground surface and an "as cast" surface is ±1-1/2 degrees.

Finish

Permanent magnet materials can be finish ground when dimensional tolerances closer than the initial manufacturing tolerances are required.

Magnets with surfaces marked "f" will be furnished with these surfaces finish ground. All other surfaces will be "as cast" or "as sintered."

Ground Surfaces

Normal tolerance between ground surface is ±.005" (.13 mm).

Perpendicularity between two ground surfaces is ±1/2 degree.

Magnetization

Unless otherwise specified, stock magnets will be furnished in a magnetized condition. The direction of magnetization is designated by ← M →. On some parts, polarity is shown as N-S. Caution: Care should be taken in handling magnetized magnets. Magnets should not be placed in repelling positions or exposed to stray ac fields as these conditions will affect their performance.

Design Considerations

Because Alnico magnets are coarse-grained, hard and brittle, they cannot be drilled or conventionally machined.

Given these mechanical properties, Alnico parts are not used as structural members. Where a choice exists, select simple shapes. Slots are preferred over holes. Cross sections of less than .125" (3.18 mm) should be avoided. Finished surfaces, when required, may be produced by grinding; however, for many applications, the "as cast" or "as sintered" surface yields a satisfactory result at a significantly lower cost.

To facilitate mounting and give adequate protection to the magnet, special assemblies such as rotors and magnetron magnets may be supplied with an aluminum jacket. Additionally, low carbon steel pole pieces may be attached to magnet pole faces by adhesive bonding or with studs or bolts. Plastisol or paint can be applied for improved appearance.

Magnetization

The most efficient use of Alnico requires that it be magnetized after the magnet has been assembled with its pole pieces into the final magnetic circuit. (Shipping the product non-magnetized also eliminates the need for special packaging, and prevents contamination by stray iron-chips, etc.)

Magnetic saturation at the end-use location requires the application of a magnetizing force 4 to 5 times greater than the coercive force of the material. For Alnico 5, 3000 oersteds (240 KA/M) are recommended. For Alnico 8, the force should be at least 7000 oersteds (560 KA/M).

The magnetizing force need be applied only momentarily. Thus, impulse magnetizers employing a capacitor discharge are commonly used. Direct current apparatus are also effective.

Stability and temperature effects

Alnico magnets offer excellent stability with respect to temperature changes: reversible change is 0.02% per degree Centigrade. Heating may produce an irreversible loss of magnet strength. The magnitude of loss depends upon the dimensions of the magnet and its composition, but is usually less than 5%, and may be recovered by remagnetization.

At temperatures exceeding 1000°F (538°C), a metallurgical change takes place which causes magnetic strength to reduce rapidly. This change will not be recovered by remagnetization.

External magnetic fields can also induce partial demagnetization. In some critical applications, it is desirable to stabilize the magnet by intentionally reducing magnetic output by 5% to 10%. Such stabilization may reduce, or even eliminate, the effect of stray external fields.

Alnico Ordering Information

Please refer to Alnico Product Specification Sheets when ordering standard Alnico permanent magnets. The magnets listed on these specification sheets, however, represent only a small percentage of the wide variety of shapes and sizes available in the various grades of Alnico. We invite your inquiries concerning magnet designs other than those listed. These inquiries should be submitted to Arnold Engineering, Marengo, Illinois, or to the nearest Arnold sales office.

It is our desire to respond to your inquiries rapidly and accurately. In order to do this, your requests should contain certain magnetic, mechanical, and general information to better serve you. Please use the Request for Quotation Form on the back of this sheet to speed the processing of your inquiry. Photocopy this form, fill it in with the necessary information, and then fax or mail to The Arnold Engineering Company.

All inquiries should include:

Inquiry reference number; part number; quantity of parts required; annual part usage; the address and person to whom the quotation should be submitted.

If a design has already been determined, your inquiry should include:

A sketch or print of the part or assembly; all dimensions and tolerances; material grade required; direction of orientation; whether the part is to be magnetized.

If you require design assistance, our staff of engineers will be happy to assist you. In addition to all of the information mentioned previously, the following would be helpful in making recommendations:

Operating point of the magnet; required flux density; physical stress placed on the magnet; demagnetizing forces; temperature range; a description of the magnetic circuit; proposed method of mounting; any application information available.

In many instances, Arnold will already have adequate tooling available to make parts to your specifications. This could result in substantial savings. It is always our goal to provide the customer with the most efficient and economical part for a given application. Detailed inquiry information will help us to achieve this.

Limited Warranty and Exclusive Remedy

The Arnold Engineering Company warrants that these products conform to industry standards specific herein and will be free from defects in material and workmanship. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ANY AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND IN LIEU OF ANY OTHER OBLIGATION ON THE PART OF THE ARNOLD ENGINEERING COMPANY. The Arnold Engineering Company will, at its option, repair or replace free of charge (excluding all shipping and handling costs) any products which have not been subject to misuse, abuse, or modification and which in its sole determination were not manufactured in compliance with the warranty given above.

THE REMEDY PROVIDED FOR HEREIN SHALL BE THE EXCLUSIVE REMEDY FOR ANY BREACH OF WARRANTY OR ANY CLAIM ARISING IN ANY WAY OUT OF THE MANUFACTURE, SALE, OR USE OF THESE PRODUCTS. In no event shall The Arnold Engineering Company and its parent company, SPS Technologies, Inc., be liable for consequential, incidental or any other damages of any nature whatsoever except those specifically provided herein for any breach of warranty or any claim arising in any way out of the manufacture, sale, or use of these products. No other person is authorized by The Arnold Engineering Company to give any other warranty, written or oral, pertaining to the products.

Request for Quotation

For 24-hour turn-around on quotations:

MAIL TO:

Customer Service
THE ARNOLD ENGINEERING COMPANY
Alnico Products Division
300 North West Street
Marengo, IL 60152

FAX TO:

(815) 568-2376

Company: _____

Inquiry No.: _____

Address: _____

Reply Requested By:

- Fax Phone
 Mail E-mail

Phone No.: _____ Fax No.: _____

Arnold Part No.: _____

E-mail: _____

Material: _____

Reply To: _____

Magnetized: _____

Application and General Information: _____

Direction of Orientation: _____

Delivery Requested: _____

Quantity/Estimated Annual Usage: _____

Print or sketch — Please include description: all dimensions and tolerances; material; magnetic requirements and material grade required; type of coating and color.



770 Linden Ave. • Rochester, NY 14625-2764 USA
Tel: 800-593-9127 • (+1) 585-385-9010 • Fax: (+1) 585-385-5625
Email: info@arnoldmagnetics.com

www.arnoldmagnetics.com