


Sintered Neodymium-Iron-Boron Magnets

These are also referred to as "Neo" or NdFeB magnets. They offer a combination of high magnetic output at moderate cost. Please contact Arnold for additional grade information and recommendations for protective coating. Assemblies using these magnets can also be provided.

Characteristic	Units	Magnetic Properties		
		min.	nominal	max.
Br , Residual Induction	Gauss	10,800	11,250	11,700
	mT	1080	1125	1170
H_{cB} , Coercivity	Oersteds	10,200	10,700	11,200
	kA/m	811	852	891
H_{cJ} , Intrinsic Coercivity	Oersteds	20,000		
	kA/m	1,592		
BH_{max} , Maximum Energy Product	MGOe	28	31	33
	kJ/m ³	223	243	263

Characteristic	Units	Thermal Properties		
		C //	C ⊥	
Reversible Temperature Coefficients ⁽¹⁾				
	of Induction, α(Br)	%/°C	-0.12	
	of Coercivity, α(H _{cj})	%/°C	-0.55	
Coefficient of Thermal Expansion ⁽²⁾	ΔL/L per °Cx10 ⁻⁶	7	-1	
Thermal Conductivity	kcal/mhr°C	5.3	5.8	
Specific Heat ⁽³⁾	cal/g°C	0.11		
Curie Temperature, T _c	°C	310		
Other Properties	Flexural Strength	psi	41,300	
		MPa	285	
	Density	g/cm ³	7.6	
	Hardness, Vickers	Hv	620	
	Electrical Resistivity, ρ	μΩ • cm	150 // 130 ⊥	

Notes: (1) Coefficients measured between 20 and 150 °C
(2) Between 20 and 200 °C. Values are typical and can vary.
(3) Between 20 and 140 °C



Notes The material data and demagnetization curves shown above represent typical properties that may vary due to product shape and size. **Demagnetization curves show nominal Br and minimum H_{cj}.** Magnets can be supplied thermally stabilized or magnetically calibrated to customer specifications. Additional grades are available. Please contact the factory for information.