

**Bonded Magnet and Magnetic Assemblies Group (BMG)**

**Product Description:** Polymer bonded, anisotropic Sr-Ferrite magnet for injection molding. Close dimensional and magnetic tolerances. Intricate shapes.

**MAGNETIC PROPERTIES @ 23°C (73°F)**

**SI CGS**

Residual Induction Br	2610 - 2890 G	261 - 289 mT
Coercive Force Hc	2170 - 2550 Oe	173 - 203 kA/m
Intrinsic Coercive Force Hci	2690 - 3150 Oe	214 - 251 kA/m
Maximum Energy Product (BH)max	1.65 – 2.11 MGOe	13.1 – 16.8 kJ/m <sup>3</sup>
Reversible Temperature Coefficient of Br	-0.11% per °F	-0.20% per °C
Reversible Temperature Coefficient of Hci	0.07% per °F	0.13% per °C
Peak Magnetizing Force Required	10,000 Oe	800 kA/m

**TYPICAL PHYSICAL PROPERTIES\* @ 23°C (73°F)**

Tensile Strength	2200 psi	15 MPa
Elongation at Break	< 2%	< 2%
Hardness	85 Shore D	85 Shore D
Density	0.13 lb/in <sup>3</sup>	3.58 g/cm <sup>3</sup>
Maximum Operating Temperature	320 °F	160 °C

(\* Reference only, not intended for specification purpose.)

