

Arnold Capabilities for Coated and Slit Silicon Steel

Magnetic Material	Three Percent Silicon Electrical Steel							
Coating Material	AISI Type C-5 - Inorganic magnesium phosphate coating with inorganic fillers and organic resin							
Characteristic	Width Range (Inch)	Tolerance (Inch unless otherwise specified)						
		Grain Oriented				ARNON™ (Non-Oriented)		
		1-mil	2-mil	4-mil	6-mil	5-mil	7-mil	
						Regular	Special	
Loss per ASTM A348 (Max.)	All Available	11.0 Watts per Pound @ 12 kG, 400 Hz	8.5 Watts per Pound @ 15 kG, 400 Hz	6.5 Watts per Pound @ 15 kG, 400 Hz	9.0 Watts per Pound @ 15 kG, 400 Hz	5.5 Watts per Pound @ 10 kG, 400 Hz	7.5 Watts per Pound @ 10 kG, 400 Hz	6.5 Watts per Pound @ 10 kG, 400 Hz
Thickness	All Available	±0.00010	±0.00015	±0.00020	±0.00030	±0.00025	±0.00035	±0.00035
Width	Up to 1.00	±0.003						
	> 1.00 and up to 9.00	±0.005						
	> 9.00 and up to 16.00	±0.010						
Burr (Maximum)	All Available	0.0001	0.0002	0.0004	0.0006	0.0005	0.0007	0.0007
Flatness (Maximum Deviation from Flat)	All Available	0.030 per Inch of Width			0.070			
Flatness Height to Length Ratio (Max.)	All Available	5%	4%	3%				
Crossbow (Maximum Deviation from Flat)	All Available	0.250			Greater of 0.100 or 0.020 per Inch of Width			
Crossbow Height to Length Ratio (Max.)	All Available	5%	4%	3%				
Coil Set (Max. in 3 ft. Vertical)	Up to 0.500	6						
	> 0.500 and up to 16.00	3						
Camber (Max. in 8 ft.)	Up to 0.250	1.50						
	> 0.250 and up to 1.500	0.50						
	> 1.500 and up to 16.00	0.25						
Coil Size (I.D. x Max. O.D.)	Less than 0.75	6 x 20						
	0.75 to 16.00	16 x 32						
Center Type	Up To 7.00	Cardboard center						
	> 7.00 and up to 16.00	Steel Center						
Coating Thickness	All Available	0.000020 to 0.000080 per side						
Average Surface Insulation Resistivity per ASTM A 717-81 (Min.)	All Available	10 Ω cm ² per lamination (two surfaces)						
Surface	All Available	Uniformly coated. Minimum surface irregularities such as creases, wrinkles, pinpricks, dents, scratches using the best practices of Arnold Rolled Products Division. Surface irregularities occur randomly; no repeating irregularities within a ten-foot section are permitted.						
Miscellaneous	All Available	Non-Oriented coils may be formed by interleaving continuous lengths. Grain Oriented coils may be formed by tape splicing. All breaks will be flagged.						
As Rolled Width available upon request.								

Arnold Capabilities for Coated and Slit Silicon Steel

Table 1. Max Coil Weights for Non-Oriented and Grain Oriented Silicon Steels		
Characteristic	Width Range (Inch)	Weight (Lbs)
Coil Weights for All Gauges	Up To 4.00	70 lbs. Max
Max Coil Weights for 1-mil (When Not Slit With Narrow Widths 4.00" or less)	> 4.00 and up to 16.00	Max 100 lbs per inch of width
Max Coil Weights for 2-mil thru 7-mil (When Not Slit With Narrow Widths 4.00" or less)	> 4.00 and up to 16.00	Max 185 lbs per inch of width
Max Coil Weights for All Gauges (When Slit Simultaneously With Narrow Slit Widths 4.00" or less)	5.00	700 lbs. Max
	6.00	840 lbs. Max
	7.00	980 lbs. Max
	8.00	1120 lbs. Max
	9.00	1,260 lbs. Max
	10.00	1,400 lbs. Max
	11.00	1,540 lbs. Max
	12.00	1,680 lbs. Max
	13.00	1,820 lbs. Max
	14.00	1,960 lbs. Max
	15.00	2,100 lbs. Max

Table 2. Recommended Grain Oriented Silicon Steel Thicknesses for Various Operating Frequency Values		
Frequency	Recommended Thickness	Approximate Induction for 300 mW/cc, 18 W/lb, 40 W/kg*
400 Hz	4-mil or 6-mil	15000 G*
1 kHz	4-mil	10000 G
2 kHz	2-mil	6000 G
5 kHz	1-mil	3000 G

*For reference only. Based on Arnold C-core data records.
 (Arnold no longer manufactures C-cores.) At 400 Hz, magnetizing current limits the maximum flux density.

Arnold Capabilities for Coated and Slit Silicon Steel

Table 3. Recommended Grain Oriented Silicon Steel Thicknesses for High-Power Pulse Operating Conditions*		
Pulse Width	Recommended Thickness	Pulses per Second
2 to 1000 microseconds	4-mil or 6-mil (D-U, U-I, L-L Laminations)	To 1000
0.25 to 2 microseconds	1-mil or 2-mil (C-Core)	To 1000
*Reference: Transformers for Electronic Circuits , Nathan R. Grossner, McGraw-Hill, New York, 1967, pp. 285 and 286, Table 11.1.		

Table 4. For Grain Oriented and Non-Oriented Silicon Steel Recommended Edge Drop For Slit Widths - All Gauges	
Recommended Edge Drop Per Side On An As Rolled Edge	0.50" minimum
Recommended Edge Drop Per Side On An As Slit Edge	0.125" minimum

Table 5. For Grain Oriented and Non-Oriented Silicon Steel - Max Number Of Breaks Per Coil			
Gauge	Width	Max Number Of Breaks	Minimum Length Between Breaks
1-mil	Up To 4"	5	100 ft.
1-mil	> 4" and up to 16" and As Rolled	5	100 ft.
2-mil	Up To 4"	4	100 ft.
2-mil	> 4" and up to 16" and As Rolled	5	100 ft.
4-mil	Up To 4"	3	100 ft.
4-mil	> 4" and up to 16" and As Rolled	4	100 ft.
5-mil	Up To 4"	3	400 ft.
5-mil	> 4" and up to 16" and As Rolled	4	400 ft.
6-mil	Up To 4"	3	100 ft.
6-mil	> 4" and up to 16" and As Rolled	4	100 ft.
7-mil	Up To 4"	3	400 ft.
7-mil	> 4" and up to 16" and As Rolled	4	400 ft.

Recent Revisions

Date	Description	Change Made By
3/31/11	Changed width max from 14.0 to 16.0 in four places on first page. Added Center Types on first page. Added Coil Weights on second page. Added Table 4 and Table 5 on third page. Renumbered tables.	Sherri Schulz