


Sintered Neodymium-Iron-Boron Magnets

These are also referred to as "Neo" or NdFeB magnets. They offer a combination of high magnetic output at moderate cost. Please contact Arnold for additional grade information and recommendations for protective coating. Assemblies using these magnets can also be provided.

Characteristic	Units	Magnetic Properties		
		min.	nominal	max.
Br , Residual Induction	Gauss	13,200	13,500	13,800
	mT	1320	1350	1380
H_{cB} , Coercivity	Oersteds	12,300	12,750	13,200
	kA/m	979	1015	1050
H_{cJ} , Intrinsic Coercivity	Oersteds	27,000		
	kA/m	2,149		
BH_{max} , Maximum Energy Product	MGOe	43	45	46
	kJ/m ³	342	354	366

Characteristic	Units	Thermal Properties		
		C //	C ⊥	
Reversible Temperature Coefficients ⁽¹⁾				
	of Induction, α(Br)	%/°C	-0.12	
	of Coercivity, α(H _{cj})	%/°C	-0.47	
Coefficient of Thermal Expansion ⁽²⁾	ΔL/L per °Cx10 ⁻⁶	7	-1	
Thermal Conductivity	kcal/mhr°C	5.3	5.8	
Specific Heat ⁽³⁾	cal/g°C	0.11		
Curie Temperature, T _c	°C	310		
Other Properties	Flexural Strength	psi	41,300	
		MPa	285	
	Density	g/cm ³	7.6	
	Hardness, Vickers	Hv	620	
	Electrical Resistivity, ρ	μΩ • cm	150 // 130 ⊥	

Notes: (1) Coefficients measured between 20 and 180 °C
 (2) Between 20 and 200 °C. Values are typical and can vary.
 (3) Between 20 and 140 °C



1 kA/m = 12.566 Oe 1 kOe = 79.577 kA/m

Notes The material data and demagnetization curves shown above represent typical properties that may vary due to product shape and size. **Demagnetization curves show nominal Br and minimum Hci.** Magnets can be supplied thermally stabilized or magnetically calibrated to customer specifications. Additional grades are available. Please contact the factory for information.